

Test Report No.: 68.431.25.2554.01

Dated: 2025-06-30



Applicant : GUANGDONG KANGLI HOUSEHOLD PRODUCTS CO.,LTD.
QIAOTOU, JIANSHAN, YASHAO TOWN,
YANGDONG, GUANGDONG PROVINCE, CHINA

Sample Description : Stainless steel slicer of SS420J2/SS301

Style No. / Name / Design No. : KL321KD

Product Type/ End use : Slice

Manufacturer : QIAOTOU, JIANSHAN, YASHAO TOWN, YANGDONG,
GUANGDONG PROVINCE, CHINA

Country of Origin : China

Test Sample Receipt Date, Location : 2025-06-23, Shenzhen

Test Period, Location : From 2025-06-24 to 2025-06-27, Shenzhen

Test Result(s) : Refer to Section 3

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : <http://www.tuv sud.cn>

Lab 1 - Chemical testing and
part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report No.: 68.431.25.2554.01

Dated: 2025-06-30



Purpose Of Examination / Conclusion:

Test Requested:	As specified by client, to test per the selected requirement(s) for the tested item(s) as stated in the Italian Ministerial Decree no° 34 21.3.1973 and its amendments, no°72,9 May,2019
------------------------	---

No.	Test Item(s)	Conclusion
1	Specific Migration of Nickel, Chromium III and Manganese	Pass

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) The test item and samples were specified by the client
- (4) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expended uncertainty for "Pass", "Fail" and "Inconclusive" is 95%.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:

Reviewed by:

Huang, Jessica
Project Manager

Shu, Steven
Project Manager



Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuv sud.com
Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China


Lab 2 - Physical & mechanical testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

1. Description of the Test Sample:

Sample Description	Stainless steel slicer of SS420J2/SS301
	

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Silvery metal big blade (SS420J2)	
T2	002	Silvery metal small blade (SS301)	

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing
 Lab 2 - Physical & mechanical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



3. Test Result

3.1 Specific Migration of Nickel, Chromium III and Manganese

Test method : Test with reference to Italian Ministerial Decree 21.03.1973 and analysed by Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES)

Test Conditions: 3% Acetic Acid: 70 °C for 0.5 Hours

TEST ITEM	RESULT [mg/kg]		Reporting limit [mg/kg]	LIMIT [mg/kg]
	SAMPLE 001 3 rd Migration	SAMPLE 002 3 rd Migration		
Manganese (Mn)	ND	ND	<0.05	0.1
Nickel (Ni)	ND	ND	<0.05	0.1
Chromium III (Cr III)	ND	ND	<0.05	0.1
Conclusion:	Pass	Pass	--	--

Note 1. "°C" denotes degree Celsius

2. "<" denotes less than

3. "mg/kg" denotes milligram per kilogram

4. "ND" denotes below the Reporting limit

5. The specification was quoted from Italian Ministerial Decree 21.03.1973

-- END OF TEST REPORT--

Regd. Office:

TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China